

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
6 December 2001 (06.12.2001)

PCT

(10) International Publication Number  
WO 01/92344 A3

(51) International Patent Classification<sup>7</sup>: C08F 8/00 (74) Agent: TACKETT, Keith, M.: Moscr. Patterson & Sheridan, LLP, 3040 Post Oak Blvd., Suite 1500. Houston, TX 77056 (US).

(21) International Application Number: PCT/US01/17582 (81) Designated States (national): JP. US.

(22) International Filing Date: 31 May 2001 (31.05.2001) (84) Designated States (regional): European patent (DE, FR).

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data: 60/208,638 1 June 2000 (01.06.2000) US  
Published:  
— with international search report

(71) Applicant (for all designated States except US): KRATON POLYMERS RESEARCH, B.V. [NL/NL]; P.O. Box 384, NL-2501 CJ The Hague (NL). (88) Date of publication of the international search report: 20 June 2002

(72) Inventor; and  
(75) Inventor/Applicant (for US only): ST. CLAIR, David, J. [US/US]; 1383 Queensbury, Houston, TX 77079 (US).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 01/92344 A3

(54) Title: COMPOSITIONS COMPRISING A FUNCTIONALIZED BLOCK COPOLYMER CROSSLINKED WITH ALUMINUM ACETYLACETONATE

(57) Abstract: In one embodiment, this invention provides a composition comprising a functionalized block copolymer crosslinked with acetylacetone. The crosslinked block copolymer has improved solvent resistance and improved cohesive strength at high temperatures. The crosslinked block copolymer comprises preferably an acid functionalized, hydrogenated block copolymer having an ABA or similar structure wherein the block comprises at least 80 wt% of a vinyl-aromatic hydrocarbon, preferably styrene, and wherein the B block comprises at least 80 wt% of a hydrogenated and conjugated diene, preferably butadiene, isoprene or a mixture thereof. In another embodiment, this invention provides an adhesive, sealant, oil gel, asphalt composition, or wax composition comprising the acid functionalized, hydrogenated block copolymer.